

PAROC BLT 3

Blowing wool



Certification Number	0809-CPR-1014 / VTT Expert Services Ltd, P.O. Box 1001, FI-02044 VTT, Finland
Designation Code	MW-EN14064-1-S1-MU1 and MW-EN14064-1-S2-MU1 for Loft
Short Description	Granulated non-combustible stone wool
Application	Thermal insulation of lofts in new and old buildings. The installation is performed by blowing wool contractors authorised by Paroc

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Packaging

Package Type	Plastic bag on pallet
--------------	-----------------------

Fire Properties

Reaction to Fire		
Property	Value	According to
Reaction to Fire, Euroclass	A1	EN 14064-1:2010 (EN 13501-1)

Continuous Glowing Combustion		
Property	Value	According to
Continuous Glowing Combustion	NPD	EN 14064-1:2010

Other Fire Properties		
Property	Value	According to
Combustibility	Non-combustible	EN ISO 1182

Thermal Properties

Thermal Properties

Property	Value	According to
Thermal Conductivity (Decl.), λ_D :		
Loft (Installed density: $\geq 33 \text{ kg/m}^3$)	0,041 W/mK	EN 14064-1:2010 (EN 12667)
Frame, slope $\leq 45^\circ$ (Installed Density: $\geq 55 \text{ kg/m}^3$)	0,036 W/mK	EN 14064-1:2010 (EN 12667)
Frame, slope $> 45^\circ$ (Installed Density: $\geq 70 \text{ kg/m}^3$)	0,036 W/mK	EN 14064-1:2010 (EN 12667)

Moisture Properties

Water Permeability		
Property	Value	According to
Water Absorption, Short Term WS, W_p	NPD	EN 14064-1:2010 (EN 1609)

Water Vapour Permeability		
Property	Value	According to
Water Vapour Transmission MU, μ	1	EN 14064-1:2010 (EN 12086)

Emissions

Release of Dangerous Substances to the Indoor Environment		
Property	Value	According to
Release of Dangerous Substances	NPD	EN 14064-1:2010

Durability

Durability of Reaction to Fire Against Ageing/Degradation

The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of product is related to the organic content, which cannot increase with time.

Durability of Thermal Resistance Against Ageing/Degradation

Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.

Settlement Class Si

Loft: 2
 Frame ($\leq 45^\circ$): 1
 Frame ($> 45^\circ$): 1

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).